

PURCHASED WOOD

September 26/2018

Studwood 9'0" Specifications Bathurst Lumber

1. **SPECIES:** Spruce, Fir, and Jack Pine
2. **AGE AT DELIVERY:** One (1) month or less from June 1st to September 30th; Two months or less remainder of the year.
3. **MINIMUM DIAMETER:** 10.12cm or 4.0" inches (inside bark)
4. **MAXIMUM DIAMETER:** 30.48 cm or 12" inches (inside bark)
5. **MINIMUM LENGTH:** 2.74 m or 108" inches, trim included. (9'foot 0" inches)
6. **MAXIMUM LENGTH:** 2.84 m or 112" inches trim included. (9'foot 4" inches)
7. **BUTT FLARE:** Limited to 5cm or 2 " from main bole.
8. **ROT:** Rot is unacceptable.
9. **RED STAIN:** Hard red stain is acceptable. White flecked red stained bolts are unacceptable and should be put into pulpwood.
10. **SWEEP:** Maximum sweep is 5cm or 2 inches per bolt of studwood.
11. **CROOK:** Excessive crook is unacceptable.
12. **FORKS:** No forks allowed.
13. **SEAMS/CAT FACES/PORCUPINE CHEWS:** Bolts exhibiting these defects greater than 2.54cm or 1" inches in depth shall be put in the pulpwood pile.
14. **MECHANICAL DAMAGE:** Splits, scarfs and other mechanical damage are unacceptable. Damaged section shall be made into pulpwood.
15. **KNOTS:** Knots must be cut flush with the body of the bolt.
16. **DEAD WOOD:** Not acceptable (characterized by dried out or bark falling off).
17. **BURNT WOOD:** Not acceptable

Spécifications pour le bois de colombage 9' pieds pour l'usine de Bathurst, N.-B.

Bois Lot Boisés Privés.

1. **Essences:** épinette, sapin et pin gris.
2. **Age pour livraison:** 1 mois entre le 1 Juin au 30 Septembre; ensuite pour le reste de l'année 2 mois.
3. **Diamètre minimum:** 10.16cm ou 4.0" pouces en dedans de l'écorce.
4. **Diamètre maximum:** 30.48cm ou 12" pouces en dedans de l'écorce.
5. **Longueur Minimum:** 2.74m ou 108" pouces. (9'pieds 0"pouces)
6. **Longueur Maximum:** 2.84m ou 112" pouces. (9'pieds 4"pouces)
7. **Contrefort:** 5cm ou 2"pouces de la bille.
8. **Pourriture:** pas acceptable.
9. **Coeur Rouge:** pas acceptable.
10. **Courbure:** 5cm ou 2" pouces par bille sur la pleine longueur est acceptable.
11. **Fourche ou bois croche:** pas acceptable.
12. **Noeuds:** les noeuds doivent être coupés le plus prêt de la bille possible.
13. **Aucun bois brûlé ou mort ne sera acceptés.**